

TAMICES DISPONIBLES PARA ESTUDIOS DE GRANULOMETRÍA

Standard Designation	Sieve Opening (mm)	Alternative Designation
100 mm	101.6	4 in.
90 mm	90.5	3-1/2 in.
75 mm	76.1	3 in.
63 mm	64	2-1/2 in.
50 mm	50.8	2 in.
45 mm	45.3	1-3/4 in.
38.1 mm	38.1	1-1/2 in.
31.5 mm	32	1-1/4 in.
25.0 mm	25.7	1 in.
22.4 mm	22.6	7/8 in.
19.0 mm	19	3/4 in.
16.0 mm	16	5/8 in.
12.5 mm	12.7	1/2 in.
11.2 mm	11.2	7/16 in.
9.5 mm	9.51	3/8 in.
8.0 mm	8	5/16 in.
6.3 mm	6.35	1/4 in.
5.6 mm	5.66	No. 3-1/2
4.75 mm	4.76	No. 4
4.00 mm	4	No. 5
3.35 mm	3.36	No. 6
2.36 mm	2.38	No. 8
2.00 mm	2	No. 10
1.70 mm	1.68	No. 12
1.40 mm	1.41	No. 14
1.18 mm	1.19	No. 16
1.00 mm	1	No. 18
850 µm	0.841	No. 20
710 µm	0.707	No. 25
600 µm	0.595	No. 30
500 µm	0.5	No. 35
425 µm	0.42	No. 40
300 µm	0.297	No. 50
250 µm	0.25	No. 60
212 µm	0.21	No. 70
180 µm	0.177	No. 80
150 µm	0.149	No. 100
125 µm	0.125	No. 120
106 µm	0.105	No. 140
90 µm	0.088	No. 170
75 µm	0.074	No. 200
63 µm	0.063	No. 230
53 µm	0.053	No. 270
45 µm	0.044	No. 325
38 µm	0.037	No. 400